

Michem® Bake 360

BRAND FAMILY OVERVIEW Fully formulated coatings for Kraft liner or folding carton stock that provide both barrier and release performance for bake-in applications such as frozen or prepared foods for bake-in applications.

USAGE Michem® Bake 360 provides excellent barrier and release performance for bake-in applications of frozen or prepared foods. It is to be used as the topcoat in a double bump system that includes Michem® Coat 84 as the base coat. This system can be applied on kraft liner or folding carton stock.

DESCRIPTION Bakery barrier and release

PHYSICAL PROPERTIES The following properties are typical but should not be considered specifications:

Appearance:	Off-white liquid
Solids Type:	Paraffin / Polyethylene Wax blend
pH:	8.5 - 9.5
Brookfield Viscosity (cps) :	100 - 500
Spindle Number:	3
RPM:	60

**SITE OF MANUFACTURE
(and PRODUCT CODE)** USA (MB360)

APPLICATION DATA Michem® Bake 360 was designed for rod application on an offline coater.

Revised 18 November 2016

The following information for this product, specific to each site of manufacture, is available upon request:

- Material Safety Data Sheets in various formats and languages (includes global chemical inventory listing)
- Food Contact Declaration of Compliance (if applicable)

Michem® Bake 360

Americas Michelman Inc. Tel: +1 513 793 7766 Fax: +1 513 793 2504	Luxembourg Michelman International SARL Tel: +352 26 39 44 1 Fax: +352 26 39 44 80	Singapore Michelman Asia-Pacific Pte. Ltd. Tel: +65 6861 2822 Fax: +65 6861 2262
China Michelman New Material (Shanghai) Co., Ltd. Tel: +86 21 3810 3800 Fax: +86 21 3810 3811	India Michelman Private Limited Tel: +91 22 6221 3800 Fax: +91 22 6221 3801/02	

The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application for our products nor anticipate every variation encountered in manufacturing equipment and methods. The products discussed are sold without warranty, express or implied and Seller disclaims any warranty of merchantability or fitness for a particular purpose in connection with the purchase of its products. It is recommended that purchasers conduct their own tests to determine the suitability of such products for their particular purpose. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent and our products are sold without warranty of non-infringement.

© 2024 MICHELMAN, INC. All rights reserved. ® Reg. U.S. Pat. TM Off.
All marks contained herein are registered or owned by Michelman, Inc.
Michelman is ISO 9001:2015 certified.