

DigiPrime® 4450

BRAND FAMILY OVERVIEW DigiPrime®, used by many digital press owners around the world because of its ability to improve ink receptivity, rub resistance, and image quality on most types of paper, plastic, and film, also provides improved productivity and efficiency for digital printing on both commercial and labels and packaging presses.

USAGE A ready to use primer which provides excellent adhesion of HP Indigo ElectroInks® to most films and papers. It has exceptional anti-block properties and can be used for two sided printing. It also has food contact approval.

DESCRIPTION Off-line primer for HP Indigo printability

PHYSICAL PROPERTIES The following properties are typical but should not be considered specifications:

Appearance:	White, translucent liquid
Non-Volatile (%) :	30.0 - 32.0
EZ Cup Viscosity (sec) :	22 - 24
Cup Number:	2
pH:	8.0 - 10.0
Brookfield Viscosity (cps) :	< 100
Spindle Number:	1
RPM:	60
Shelf Life (months) :	The product has a shelf life of 12 months from date of manufacture when storage and handling instructions are followed.

**SITE OF MANUFACTURE
(and PRODUCT CODE)** Singapore (DP4450.S)

APPLICATION DATA DigiPrime® 4450 may be applied by flexo or gravure coating systems. Recommended application rate for films is between 0.5 to 0.2 gsm dry coat weight. For paper, slightly higher weights will be needed to overcome the absorption of the substrate, this will vary from paper to paper but dry weights around 0.7 to 1 gsm are recommended. EZ Cup Viscosity - #2 Cup, 22 - 24 sec.

Revised 18 April 2017

The following information for this product, specific to each site of manufacture, is available upon request:

- Material Safety Data Sheets in various formats and languages (includes global chemical inventory listing)
- Food Contact Declaration of Compliance (if applicable)

DigiPrime® 4450

Americas Michelman Inc. Tel: +1 513 793 7766 Fax: +1 513 793 2504	Luxembourg Michelman International SARL Tel: +352 26 39 44 1 Fax: +352 26 39 44 80	Singapore Michelman Asia-Pacific Pte. Ltd. Tel: +65 6861 2822 Fax: +65 6861 2262
China Michelman New Material (Shanghai) Co., Ltd. Tel: +86 21 3810 3800 Fax: +86 21 3810 3811	India Michelman Private Limited Tel: +91 22 6221 3800 Fax: +91 22 6221 3801/02	

The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application for our products nor anticipate every variation encountered in manufacturing equipment and methods. The products discussed are sold without warranty, express or implied and Seller disclaims any warranty of merchantability or fitness for a particular purpose in connection with the purchase of its products. It is recommended that purchasers conduct their own tests to determine the suitability of such products for their particular purpose. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent and our products are sold without warranty of non-infringement.

© 2024 MICHELMAN, INC. All rights reserved. ® Reg. U.S. Pat. TM Off.
All marks contained herein are registered or owned by Michelman, Inc.
Michelman is ISO 9001:2015 certified.