

# Michem® Flex B7010

---

**USAGE** A transparent high oxygen barrier water-based coating designed primarily for offline applications of polymer materials. It is more durable and can withstand fracturing and pinholes compared to traditional barrier coatings. It can also be combined with metallization processes as a protective oxygen barrier coating.

**DESCRIPTION** Transparent oxygen barrier coating for offline flexible packaging coating applications

**PHYSICAL PROPERTIES** The following properties are typical but should not be considered specifications:

Appearance:	Clear, yellow to brown liquid
Freeze/Thaw Stability:	None: protect from freezing
Non-Volatile (%) :	9.5 - 10.5
Specific Gravity:	0.99 - 1.01
pH:	3.0 - 6.0
Brookfield Viscosity (cps) :	0 - 100
Spindle Number:	1
RPM:	60
Shelf Life (months) :	The product has a shelf life of 12 months from date of manufacture when storage and handling instructions are followed.

**SITE OF MANUFACTURE (and PRODUCT CODE)** Singapore (MFB7010.S)

**APPLICATION DATA** Michem® Flex B7010 is designed to be applied offline to polymer materials using gravure or flexographic coating processes. Suggested coat weight is 0.3 dry gsm. At the recommended coating weight, the dried coating is transparent, non-blocking and contributes to oxygen barrier properties of polymer materials. It should be used undiluted and dried thoroughly after application. This product was specifically designed for and is available only in Asia.

**STORAGE** Keep containers tightly closed in a dry, cool and well-ventilated place. Keep from freezing.

**HANDLING** Handle in accordance with good industrial hygiene and safety practice. Use personal protective equipment as required.

# Michem® Flex B7010

---

Revised 05 December 2018

The following information for this product, specific to each site of manufacture, is available upon request:

- Material Safety Data Sheets in various formats and languages (includes global chemical inventory listing)
- Food Contact Declaration of Compliance (if applicable)

---

## Americas

Michelman Inc.  
Tel: +1 513 793 7766  
Fax: +1 513 793 2504

## China

Michelman New Material  
(Shanghai) Co., Ltd.  
Tel: +86 21 2098 6880  
Fax: +86 21 3810 3811

## India

Michelman Private Limited  
(formerly known as  
Michelman Chemicals Pvt Ltd)  
Tel: +91 22 28672783  
Fax: +91 22 28672784

## Japan

Michelman Japan LLC  
Tel: +81 3 45 80 14 90  
Fax: +81 3 45 80 27 01

## Luxembourg

Michelman SARL  
Tel: +352 26 39 44 1  
Fax: +352 26 39 44 80

## Singapore

Michelman Asia-Pacific Pte. Ltd.  
Tel: +65 6861 2822  
Fax: +65 6861 2262

---

The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application for our products nor anticipate every variation encountered in manufacturing equipment and methods. The products discussed are sold without warranty, express or implied and Seller disclaims any warranty of merchantability or fitness for a particular purpose in connection with the purchase of its products. It is recommended that purchasers conduct their own tests to determine the suitability of such products for their particular purpose. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent and our products are sold without warranty of non-infringement.

© 2020 MICHELMAN, INC. All rights reserved. ® Reg. U.S. Pat. TM Off.  
All marks contained herein are registered or owned by Michelman, Inc.  
Michelman is ISO 9001:2015 certified.