

ProHere® L 90009

BRAND FAMILY OVERVIEW ProHere® grades are waterborne polymer dispersions and emulsions specifically developed for use in metal coatings. The range encompasses both polymer resins that can serve as organic binders in a coating formulation as well as lubricants and anti-scratch additives for metal processing and in-use lubricants.

USAGE Imparts enhanced lubricity, abrasion resistance, scratch resistance and torque/tension control to metal coatings.

DESCRIPTION Nonionic polyethylene emulsion

PERFORMANCE ATTRIBUTES This product is used in many applications including the following:

Market	Properties Imparted
Can & Coil	mar resistance, scratch resistance
General Metal	abrasion resistance, enhanced lubricity, scratch resistance, torque/tension control

PHYSICAL PROPERTIES The following properties are typical but should not be considered specifications:

Appearance:	Translucent liquid
Solids Type:	High Density Polyethylene
Emulsifier Charge:	Nonionic
Non-Volatile (%) :	34.5 - 35.5
pH:	8.5 - 10.5
Recommended pH of your system:	> 7.0
Brookfield Viscosity (cps) :	< 50
Spindle Number:	1
RPM:	60

SITE OF MANUFACTURE (and PRODUCT CODE) USA (PH90009L), Singapore (PH90009L.S)

Revised 12 July 2018

The following information for this product, specific to each site of manufacture, is available upon request:

- Material Safety Data Sheets in various formats and languages (includes global chemical inventory listing)
- Food Contact Declaration of Compliance (if applicable)

ProHere® L 90009

Americas

Michelman Inc.
Tel: +1 513 793 7766
Fax: +1 513 793 2504

China

Michelman (Shanghai)
Chemical Trading Co., Ltd.
Tel: +86 21 2098 6880
Fax: +86 21 2098 6881

India

Michelman Private Limited
(formerly known as
Michelman Chemicals Pvt Ltd)
Tel: +91 22 28672783
Fax: +91 22 28672784

Japan

Michelman Japan LLC
Tel: +81 3 45 80 14 90
Fax: +81 3 45 80 27 01

Luxembourg

Michelman SARL
Tel: +352 26 39 44 1
Fax: +352 26 39 44 80

Singapore

Michelman Asia-Pacific Pte. Ltd.
Tel: +65 6861 2822
Fax: +65 6861 2262

The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application for our products nor anticipate every variation encountered in manufacturing equipment and methods. The products discussed are sold without warranty, express or implied and Seller disclaims any warranty of merchantability or fitness for a particular purpose in connection with the purchase of its products. It is recommended that purchasers conduct their own tests to determine the suitability of such products for their particular purpose. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent and our products are sold without warranty of non-infringement.

© 2018 MICHELMAN, INC. All rights reserved. ® Reg. U.S. Pat. TM Off.
All marks contained herein are registered or owned by Michelman, Inc.
Michelman is ISO 9001:2015 certified.