

VaporCoat® 2200R

BRAND FAMILY OVERVIEW VaporCoat® recyclable water-based coatings confer high barrier to paper-based packaging and wraps. Most VaporCoat grades are designed for “low MVTR”, to retard water vapor transmission in order to keep perishables fresh, frozen goods intact, or sensitive contents in factory condition. In response to market interest for greater food safety and preservation, additional VaporCoat products can inhibit contaminants ordinarily found in recycled paper from migrating into packaged dry food.

USAGE A coating which provides water and grease resistance and excellent MVTR properties on kraft liner and other substrates. When properly applied over a base coat, this repulpable coating is recommended as a replacement for some curtain coating applications, poly-laminated board and plastic bags.

DESCRIPTION MVTR, water and grease resistance coating

PERFORMANCE ATTRIBUTES This product is used in many applications including the following:

Market	Properties Imparted
Food Service	grease & oil resistance, MVTR, water resistance
Industrial	grease & oil resistance, MVTR
Perishables	MVTR, release with barrier

PHYSICAL PROPERTIES The following properties are typical but should not be considered specifications:

Appearance:	Off-white liquid
Solids Type:	Polymer
Non-Volatile (%) :	38.5 - 39.5
pH:	8.2 - 9.2
Brookfield Viscosity (cps) :	100 - 600
Spindle Number:	3
RPM:	60

SITE OF MANUFACTURE (and PRODUCT CODE) USA (VAP2200R)

APPLICATION DATA VaporCoat® 2200R is best applied by rod coater at a rate of 4-7 wet pounds per MSF and as a pre-applied coating or in-line at the wet end of the corrugator or by blade, flexo or gravure at the dry end of the corrugator. EZ Cup Viscosity = 9 - 20seconds, #3 Cup.

VaporCoat® 2200R

STORAGE Keep containers tightly closed in a dry, cool and well-ventilated place. Keep from freezing.

HANDLING Handle in accordance with good industrial hygiene and safety practice. Use personal protective equipment as required.

Revised 12 May 2017

The following information for this product, specific to each site of manufacture, is available upon request:

- Material Safety Data Sheets in various formats and languages (includes global chemical inventory listing)
- Food Contact Declaration of Compliance (if applicable)

Americas

Michelman Inc.
Tel: +1 513 793 7766
Fax: +1 513 793 2504

China

Michelman New Material
(Shanghai) Co., Ltd.
Tel: +86 21 2098 6880
Fax: +86 21 3810 3811

India

Michelman Private Limited
(formerly known as
Michelman Chemicals Pvt Ltd)
Tel: +91 22 28672783
Fax: +91 22 28672784

Japan

Michelman Japan LLC
Tel: +81 3 45 80 14 90
Fax: +81 3 45 80 27 01

Luxembourg

Michelman SARL
Tel: +352 26 39 44 1
Fax: +352 26 39 44 80

Singapore

Michelman Asia-Pacific Pte. Ltd.
Tel: +65 6861 2822
Fax: +65 6861 2262

The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application for our products nor anticipate every variation encountered in manufacturing equipment and methods. The products discussed are sold without warranty, express or implied and Seller disclaims any warranty of merchantability or fitness for a particular purpose in connection with the purchase of its products. It is recommended that purchasers conduct their own tests to determine the suitability of such products for their particular purpose. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent and our products are sold without warranty of non-infringement.

© 2019 MICHELMAN, INC. All rights reserved. ® Reg. U.S. Pat. TM Off.
All marks contained herein are registered or owned by Michelman, Inc.
Michelman is ISO 9001:2015 certified.