

DigiPrime® 060

BRAND FAMILY OVERVIEW DigiPrime®, used by many digital press owners around the world because of its ability to improve ink receptivity, rub resistance, and image quality on most types of paper, plastic, and film, also provides improved productivity and efficiency for digital printing on both commercial and labels and packaging presses.

USAGE Imparts a print-receptive surface to paperboard and metalized paperboard substrates to improve the transfer and adhesion of HP Indigo Electroinks. It is used in the in-line priming unit available on the HP Indigo 30000 and 35K Digital Presses.

DESCRIPTION Primer for digital printing

PHYSICAL PROPERTIES The following properties are typical but should not be considered specifications:

| | |
|------------------------------|---|
| Appearance: | Clear liquid |
| Non-Volatile (%) : | 4.0 - 5.0 |
| pH: | 9.5 - 11.4 |
| Brookfield Viscosity (cps) : | 3 - 30 |
| Spindle Number: | 1 |
| RPM: | 60 |
| Shelf Life (months) : | The product has a shelf life of 24 months from date of manufacture when storage and handling instructions are followed. |

SITE OF MANUFACTURE (and PRODUCT CODE) USA (DP060), Belgium (DP060.E), Singapore (DP060.S)

APPLICATION DATA Indigo 30000 and 35K Digital Press Defoaming : In the event of foam development, small amounts of suitable antifoam are recommended. Please refer to Michelman for suitable antifoam grade and usage. Clean up: Clean up must be accomplished with soft water while the applicator roll is still damp. In case the primer dries, residue may be cleaned by scrubbing with soap and water. For hard residues, a mix of caustic solution might be used. Do not dilute.

Revised 20 November 2024

The following information for this product, specific to each site of manufacture, is available upon request:

- Material Safety Data Sheets in various formats and languages (includes global chemical inventory listing)
- Food Contact Declaration of Compliance (if applicable)

DigiPrime® 060

Americas

Michelman Inc.
Tel: +1 513 793 7766
Fax: +1 513 793 2504

Luxembourg

Michelman International SARL
Tel: +352 26 39 44 1
Fax: +352 26 39 44 80

Singapore

Michelman Asia-Pacific Pte. Ltd.
Tel: +65 6861 2822
Fax: +65 6861 2262

China

Michelman New Material
(Shanghai) Co., Ltd.
Tel: +86 21 3810 3800
Fax: +86 21 3810 3811

India

Michelman Private Limited
Tel: +91 22 6221 3800
Fax: +91 22 6221 3801/02

The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application for our products nor anticipate every variation encountered in manufacturing equipment and methods. The products discussed are sold without warranty, express or implied and Seller disclaims any warranty of merchantability or fitness for a particular purpose in connection with the purchase of its products. It is recommended that purchasers conduct their own tests to determine the suitability of such products for their particular purpose. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent and our products are sold without warranty of non-infringement.

© 2025 MICHELMAN, INC. All rights reserved. ® Reg. U.S. Pat. TM Off.
All marks contained herein are registered or owned by Michelman, Inc.
Michelman is ISO 9001:2015 certified.