

Hydrosize® HP3-02

BRAND FAMILY OVERVIEW Our Hydrosize® line of products includes sizing solutions designed for use in the manufacturing of glass fiber, carbon fiber and natural fiber, including both chopped and continuous formats of those fibers. These are in turn used to manufacture composite products and components.

USAGE Designed for use as a fiber sizing coating, this product offers excellent adhesion, a high Tg and is APE free.

DESCRIPTION Phenoxy dispersion

PERFORMANCE ATTRIBUTES This product is used in many applications including the following:

larket	Properties Imparted
iber Sizing	chopped strands, PA compatible, PC compatible, PET/PBT compatible, PPS/ETP compatible, thermal stability, thermosets compatible

PHYSICAL PROPERTIES The following properties are typical but should not be considered specifications:

Appearance:	Milky white
Solids Type:	Phenoxy Dispersion
Emulsifier Charge:	Anionic / Nonionic
Non-Volatile (%) :	30.0 - 33.0
pH:	6.5 - 8.5
Recommended pH of your system:	> 5.0
Brookfield Viscosity (cps):	< 4000
Spindle Number:	4
RPM:	60

SITE OF MANUFACTURE USA (HP302) (and PRODUCT CODE)

STORAGE Keep containers tightly closed in a dry, cool and well-ventilated place. Keep from freezing. Keep out of the reach of children. Store locked up.

> page 1 www.michelman.com



Hydrosize® HP3-02

HANDLING Avoid contact with skin, eyes or clothing. Do not eat, drink or smoke when using this product. Ensure adequate ventilation. Handle in accordance with good industrial hygiene and safety practice. In case of insufficient ventilation, wear suitable respiratory equipment. Take off contaminated clothing and wash before reuse. Use personal protection equipment.

Revised 03 August 2020

The following information for this product, specific to each site of manufacture, is available upon request:

- Material Safety Data Sheets in various formats and languages (includes global chemical inventory listing)
- Food Contact Declaration of Compliance (if applicable)

Americas

Michelman Inc. Tel: +1 513 793 7766 Fax: +1 513 793 2504

China

Michelman New Material (Shanghai) Co., Ltd. Tel: +86 21 3810 3800 Fax: +86 21 3810 3811

Luxembourg

Michelman International SARL Tel: +352 26 39 44 1 Fax: +352 26 39 44 80

India

Michelman Private Limited Tel: +91 22 6221 3800 Fax: +91 22 6221 3801/02

Singapore

Michelman Asia-Pacific Pte. Ltd. Tel: +65 6861 2822 Fax: +65 6861 2262

The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application for our products nor anticipate every variation encountered in manufacturing equipment and methods. The products discussed are sold without warranty, express or implied and Seller disclaims any warranty of merchantability or fitness for a particular purpose in connection with the purchase of its products. It is recommended that purchasers conduct their own tests to determine the suitability of such products for their particular purpose. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent and our products are sold without warranty of non-infringement.

© 2025 MICHELMAN, INC. All rights reserved. ® Reg. U.S. Pat. TM Off. All marks contained herein are registered or owned by Michelman, Inc. Michelman is ISO 9001:2015 certified.

page 2 www.michelman.com