

Michem® Emulsion 42035A

BRAND FAMILY OVERVIEW Michem® Emulsion is a versatile family of products that adds value to a wide range of markets. These markets include paint & coatings, fiberglass, inks & OPVs, floor care, wood finishes, automotive care products, building products, carpets, die lubricants, textiles and urethane foam.

USAGE This film former for fiberglass sizing formulations is used to reinforce polypropylene. It provides an excellent balance between mechanical properties and color and is suitable for sizings for chopped strands as well as for continuous

DESCRIPTION Polypropylene emulsion

PERFORMANCE ATTRIBUTES This product is used in many applications including the following:

Market	Properties Imparted
Fiber Sizing	chopped strands

PHYSICAL PROPERTIES The following properties are typical but should not be considered specifications:

Appearance:	Off-white to yellow liquid
Solids Type:	Polypropylene
Emulsifier Charge:	Cationic/ Nonionic
Freeze/Thaw Stability:	None: protect from freezing
Non-Volatile (%) :	34.5 - 35.5
Specific Gravity:	0.97 - 0.99
pH:	3.5 - 6.5
Recommended pH of your system:	< 7.0
Brookfield Viscosity (cps) :	< 30
Spindle Number:	1
RPM:	60

(and PRODUCT CODE)

SITE OF MANUFACTURE Belgium (ME42035A.E)

HANDLING Avoid contact with eyes, skin and clothing. Ensure adequate ventilation. Handle in accordance with good industrial hygiene and safety practice. If this product contains synthetic polymer microparticles, ensure that the product is not released to the environment. If applicable, the product should be mixed in closed containers to prevent a release of synthetic polymer microparticles into the environment.

> page 1 www.michelman.com



Michem® Emulsion 42035A

Revised 08 June 2023

The following information for this product, specific to each site of manufacture, is available upon request:

- Material Safety Data Sheets in various formats and languages (includes global chemical inventory listing)
- Food Contact Declaration of Compliance (if applicable)

Americas

Michelman Inc. Tel: +1 513 793 7766 Fax: +1 513 793 2504

China

Michelman New Material (Shanghai) Co., Ltd. Tel: +86 21 3810 3800 Fax: +86 21 3810 3811

Luxembourg

Michelman International SARL Tel: +352 26 39 44 1 Fax: +352 26 39 44 80

India

Michelman Private Limited Tel: +91 22 6221 3800 Fax: +91 22 6221 3801/02

Singapore

Michelman Asia-Pacific Pte. Ltd. Tel: +65 6861 2822 Fax: +65 6861 2262

The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application for our products nor anticipate every variation encountered in manufacturing equipment and methods. The products discussed are sold without warranty, express or implied and Seller disclaims any warranty of merchantability or fitness for a particular purpose in connection with the purchase of its products. It is recommended that purchasers conduct their own tests to determine the suitability of such products for their particular purpose. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent and our products are sold without warranty of non-infringement.

© 2025 MICHELMAN, INC. All rights reserved. ® Reg. U.S. Pat. TM Off. All marks contained herein are registered or owned by Michelman, Inc. Michelman is ISO 9001:2015 certified

page 2 www.michelman.com