

# Michem® Flex B1000

---

**USAGE** Designed to provide a high level of mineral oil and oxygen barrier and is printable and cold set gluable.

**DESCRIPTION** Water-based mineral oil migration and oxygen barrier coating for paper

**PHYSICAL PROPERTIES** The following properties are typical but should not be considered specifications:

Appearance:	Off-white liquid
Solids Type:	Formulated Polymer
Freeze/Thaw Stability:	None: protect from freezing
Non-Volatile (%) :	17.0 - 19.5
Specific Gravity:	0.99 - 1.09
pH:	5.5 - 7.5
Brookfield Viscosity (cps) :	300 - 700
Spindle Number:	3
RPM:	60
Shelf Life (months) :	The product has a shelf life of 3 months from date of manufacture when storage and handling instructions are followed.

**SITE OF MANUFACTURE (and PRODUCT CODE)** Singapore (MFB1000.S)

**APPLICATION DATA** Michem® Flex B1000 can be applied via rod, blade, flexo or gravure.

Revised 26 November 2018

- The following information for this product, specific to each site of manufacture, is available upon request:
- Material Safety Data Sheets in various formats and languages (includes global chemical inventory listing)
  - Food Contact Declaration of Compliance (if applicable)

# Michem® Flex B1000

---

## Americas

Michelman Inc.  
Tel: +1 513 793 7766  
Fax: +1 513 793 2504

## China

Michelman New Material  
(Shanghai) Co., Ltd.  
Tel: +86 21 2098 6880  
Fax: +86 21 3810 3811

## India

Michelman Private Limited  
(formerly known as  
Michelman Chemicals Pvt Ltd)  
Tel: +91 22 28672783  
Fax: +91 22 28672784

## Japan

Michelman Japan LLC  
Tel: +81 3 45 80 14 90  
Fax: +81 3 45 80 27 01

## Luxembourg

Michelman SARL  
Tel: +352 26 39 44 1  
Fax: +352 26 39 44 80

## Singapore

Michelman Asia-Pacific Pte. Ltd.  
Tel: +65 6861 2822  
Fax: +65 6861 2262

The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application for our products nor anticipate every variation encountered in manufacturing equipment and methods. The products discussed are sold without warranty, express or implied and Seller disclaims any warranty of merchantability or fitness for a particular purpose in connection with the purchase of its products. It is recommended that purchasers conduct their own tests to determine the suitability of such products for their particular purpose. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent and our products are sold without warranty of non-infringement.

© 2021 MICHELMAN, INC. All rights reserved. ® Reg. U.S. Pat. TM Off.  
All marks contained herein are registered or owned by Michelman, Inc.  
Michelman is ISO 9001:2015 certified.