

Michem® Wood Coating 44

BRAND FAMILY OVERVIEW Michem® Wood Coating products are low-VOC and set the water resistance standard for waterborne deck stains and sealants. Providing great versatility for exterior wood protection, each solution in Michelman's line of topical wood treatment additives passes the ASTMD-4446 standard for swell resistance.

USAGE Penetrating deep into wood substrates this user-friendly, water resistant topical wood treatment provides good water beading and swell resistance with lower VOC for exterior wood decks, fences, and garden sheds. Michem® Wood coating 44 produces a natural surface appearance and is particularly suitable for softwood as well as extending the look and use of outdoor wood furniture.

DESCRIPTION Proprietary Emulsion

PERFORMANCE ATTRIBUTES This product is used in many applications including the following:

Market	Properties Imparted
Exterior Wood Protection	<i>swell resistance, water beading</i>

PHYSICAL PROPERTIES

The following properties are typical but should not be considered specifications:

Appearance:	White liquid
Solids Type:	Proprietary
Emulsifier Charge:	Anionic
Non-Volatile (%):	43.5 - 44.5
pH:	8.0 - 10.0
Recommended pH of your system:	> 7.0
Brookfield Viscosity (cps):	< 500
Spindle Number:	2
RPM:	60

SITE OF MANUFACTURE Belgium (MWC44.E)
(and PRODUCT CODE)

STORAGE Keep containers tightly closed in a dry, cool and well-ventilated place. Keep from freezing.

HANDLING Handle in accordance with good industrial hygiene and safety practice. Use personal protective equipment as required.

Michem® Wood Coating 44

Revised 27 November 2023

The following information for this product, specific to each site of manufacture, is available upon request:

- Material Safety Data Sheets in various formats and languages (includes global chemical inventory listing)
- Food Contact Declaration of Compliance (if applicable)

Americas

Michelman Inc.
Tel: +1 513 793 7766
Fax: +1 513 793 2504

Luxembourg

Michelman International SARL
Tel: +352 26 39 44 1
Fax: +352 26 39 44 80

Singapore

Michelman Asia-Pacific Pte. Ltd.
Tel: +65 6861 2822
Fax: +65 6861 2262

China

Michelman New Material
(Shanghai) Co., Ltd.
Tel: +86 21 3810 3800
Fax: +86 21 3810 3811

India

Michelman Private Limited
Tel: +91 22 6221 3800
Fax: +91 22 6221 3801/02

The facts stated and the recommendations contained herein are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application for our products nor anticipate every variation encountered in manufacturing equipment and methods. The products discussed are sold without warranty, express or implied and Seller disclaims any warranty of merchantability or fitness for a particular purpose in connection with the purchase of its products. It is recommended that purchasers conduct their own tests to determine the suitability of such products for their particular purpose. Seller shall not be liable for any injury, loss or damage, direct or consequential arising out of the use of or the inability to use the product. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent and our products are sold without warranty of non-infringement.

© 2026 MICHELMAN, INC. All rights reserved. ® Reg. U.S. Pat. TM Off.

All marks contained herein are registered or owned by Michelman, Inc.

Michelman is ISO 9001:2015 certified.